

*Anexa – Rezultatele determinarilor concentratiilor elementale prin metoda XRF  
asupra obiectelor de bronz descoperite la Racari*

<i>Nr. Inv.</i>	<i>Obiect</i>	<i>Cu(%)</i>	<i>Zn(%)</i>	<i>Sn(%)</i>	<i>Pb(%)</i>	<i>Ag(%)</i>	<i>Alte elemente</i>	<i>Tip aliaj</i>
<b>156</b>	<i>Moneda argint Severus Alexandru</i>	4.5	-	5.0	2.0	88.0	Au, Hg	argint
<b>2001</b>	<i>Moneda argint Iulia Mamaea</i>	77.0	-	2.5	1.5	19.0	Fe	billon
<b>298</b>	<i>Moneda argint Filip Arabul</i>	30.0	-	2.5	-	67.0	Fe, Hg, Au: 0.15%	billon
<b>72</b>	<i>Monedă bronz Hadrianus (?)</i>	80.0	8	10.0	2.0	0.2	Fe, As	bronz
<b>192</b>	<i>Piesa de echipament militar de bronz, rectangulara</i>	82.0	4.0	10.0	1.0	0.2	Fe: 2.0%, As: 0.15%	bronz
<b>222</b>	<i>Moneda bronz A. Pius</i>	95.0	3.5	0.5	-	0.1	As,Fe: 0.3	bronz
<b>299</b>	<i>Alta moneda - bronz - Severus Alexandru</i>	98.0	-	1.5	0.15	0.1	Fe	cupru
<b>169</b>	<i>Moneda bronz Sev. Al.</i>	97.0	-	2.0	0.3	0.15	As: 0.3%, Fe: 0.5 %	cupru
<b>162</b>	<i>Moneda bronz Elagabal</i>	87.0	-	12.5	0.25	0.1	As, Fe	bronz
<b>122</b>	<i>Moneda bronz Filip Arabul</i>	96.0	-	3.5	0.1	urme	As: 0.2%	cupru
<b>2004</b>	<i>Moneda bronz Gordian</i>	95.0	-	0.8	1.5	2.0	As: 0.5%	bronz
<b>237</b>	<i>Moneda bronz Herennia Etruscilla</i>	97.0	-	1.5	1.5	urme	As	cupru
<b>2006</b>	<i>Pensetă</i>	80.5	-	16.0	1.5	urme	Fe: 1.0%	bronz
<b>70</b>	<i>Fragment piesa bronz</i>	97.0	2.5	urme	urme	urme	As, Fe: 0.3%	alama
<b>101</b>	<i>Fragment bratară de bronz</i>	77.0	-	20.0	1.5	0.4	Fe: 0.5%, As: 0.5%	bronz
<b>83</b>	<i>Pandantiv de bronz</i>	96.0	3.0	urme	0.3	0.1	Fe: 0.5%	bronz
<b>65</b>	<i>Bratară de bronz fragmentară</i>	63.0	2.0	20.0	14.0	urme	-	bronz
<b>245</b>	<i>Veriga bronz</i>	78.0	1.5	8.0	1.0	2.0	Fe	bronz
<b>226</b>	<i>Fibula bronz</i>	47.0	urme	28.0	23.0	0.2	Fe: 1.5%	bronz
<b>261</b>	<i>Fibula bronz</i>	95.0	-	4.0	0.5	urme		bronz
<b>264</b>	<i>Veriga bronz fragmentară</i>	47.0	0.5	40.0	10.0	urme	Fe: 2.0%	bronz